

INDEX 1965 - 1966

TECHNICAL SERVICE BULLETINS

SECTION E

Bulletin
Number

Model
Range

Subject

1 E 1

All Models

Paint Rectification



TECHNICAL SERVICE BULLETIN

The British Motor Corporation / Hambro Inc.

734 GRAND AVENUE, RIDGEFIELD, NEW JERSEY 07657

September 30, 1966

TO ALL DISTRIBUTORS AND DEALERS

Re: Paint Rectification

All Models

To assist in rectification of paintwork in the field, a full range of paints, matching B.M.C. colors may be obtained from the following manufacturers:-

Dupont

Rinshed-Mason

East Coast Specialties Corp.
(Distributors for Imperial Chemical
Industries Paints).

Attached is a Color/Model reference sheet incorporating Rinshed-Mason's formulae numbers.

In addition, a breakdown of each color formulae for per-max and lacquer finish is incorporated.

In the event of any difficulty being experienced in obtaining matching colors, these formulae breakdown may be presented to any Rinshed-Mason jobber.

INTERMIXING FORMULAEBMC 1965/1967 LACQUER FORMULAE

| | | |
|--|--|---|
| <u>Grampian Gray</u> <u>U1287</u> 100 Lacquer Thinner 100 447 30901 547 412 30401 959 28 30307 987 13 30704 1000 | <u>Florida Green</u> <u>U3476</u> 100 Lacquer Thinner 100 795 30901 895 37 30708 932 35 30402 967 33 30306 1000 | <u>Healey Blue</u> <u>U2869</u> 100 PNT-90 100 663 30102 763 206 30207 969 21 30607 990 10 30401 1000 |
| <u>Stone</u> <u>U1471</u> 100 Lacquer Thinner 100 67 30901 736 180 30401 924 39 30802 963 37 30704 1000 | <u>Smoke Gray</u> <u>U1310</u> 100 Lacquer Thinner 100 762 30901 862 101 30401 963 23 30708 986 12 30306 998 2 30203 1000 | <u>Sherwood Green</u> <u>U3785</u> 100 Lacquer Thinner 100 457 30401 557 328 30901 885 94 30704 979 21 30306 1000 |
| <u>British Racing Green</u> <u>U3876</u> 100 Lacquer Thinner 100 327 30201 427 318 30701 745 214 30401 959 41 30901 1000 | <u>Chalk Blue</u> <u>U2918</u> 100 PNT-90 100 485 30901 585 224 30401 809 61 30607 870 34 30204 904 96 30001 1000 | <u>Colorado Red</u> <u>U5623R</u> 100 Lacquer Thinner 100 606 30506 706 167 30710 873 67 30901 940 60 30402 1000 |
| <u>Maltase White</u> <u>U9979</u> 100 PNT-90 100 812 30901 912 49 30708 961 39 30402 1000 | <u>Maroon</u> <u>U631M</u> 100 Lacquer Thinner 100 810 30604 910 35 30401 945 35 30901 980 20 30702 1000 | <u>Mineral Blue</u> <u>U2957</u> 100 PNT-90 100 284 30204 384 163 30901 547 68 30401 615 385 30001 1000 |
| <u>Old English White</u> <u>U9938</u> 100 Lacquer Thinner 100 308 30901 908 48 30708 956 40 30402 996 4 30707 1000 | <u>Pale Primrose</u> <u>U7480</u> 100 Lacquer Thinner 100 726 30901 826 98 30708 924 64 30707 988 12 30402 1000 | <u>Riviera Blue</u> <u>U2745</u> 100 Lacquer Thinner 100 495 30901 595 164 30203 759 154 30204 913 87 30401 1000 |

INTERMIXING FORMULAEBMC 1966/1967 LACQUER FORMULAE

| | | |
|--|---|--|
| <p style="text-align: center;"><u>Sandy Beige</u> <u>U8985</u></p> <p>100 Lacquer Thinner 100 771 30901 871 90 30401 961 37 30802 998 2 30707 1000</p> | <p style="text-align: center;"><u>Surf Blue</u> <u>U2611</u></p> <p>100 Lacquer Thinner 100 715 30901 815 72 30203 887 62 30306 949 51 30401 1000</p> | <p style="text-align: center;"><u>Feat</u> <u>U8986</u></p> <p>100 Lacquer Thinner 100 365 30901 465 335 30401 800 160 30802 960 40 30704 1000</p> |
| <p style="text-align: center;"><u>Tartan Red</u> <u>U5596R</u></p> <p>100 Lacquer Thinner 100 883 30503 983 17 30603 1000</p> | <p style="text-align: center;"><u>Almond Green</u> <u>U3774</u></p> <p>100 Lacquer Thinner 100 309 30401 409 283 30901 692 193 30704 885 115 30306 1000</p> | <p style="text-align: center;"><u>Connaught Green</u> <u>48A33</u></p> <p>100 Lacquer Thinner 100 580 30401 680 210 30201 890 85 30702 975 25 30901 1000</p> |
| <p style="text-align: center;"><u>Fiesta Yellow</u> <u>U7268</u></p> <p>100 Lacquer Thinner 100 815 30901 915 58 30707 973 23 30401 996 4 30308 1000</p> | <p style="text-align: center;"><u>Island Blue</u> <u>U2314</u></p> <p>100 Lacquer Thinner 100 385 30901 485 260 30401 745 200 30203 945 55 30603 1000</p> | <p style="text-align: center;"><u>Carlton Gray</u> <u>U1509</u></p> <p>100 Lacquer Thinner 100 547 30401 647 230 30901 877 101 30205 978 22 30308 1000</p> |
| | <p style="text-align: center;"><u>Tweed Gray</u> <u>U1176</u></p> <p>100 Lacquer Thinner 100 561 30901 661 206 30401 867 88 30205 955 45 30704 1000</p> | |

INTERMIXING FORMULAEBMC 1966/1967 PER-MAX FORMULAE

| | | | | | | | | |
|---------------------------------------|-------|------|--------------------------------------|-------|------|---|-------|------|
| <u>Sandy Beige</u> <u>2U8985</u> | | | <u>Surf Blue</u> <u>2U2611</u> | | | <u>Paas</u> <u>2U8986</u> | | |
| 100 | TE-01 | 100 | 100 | TE-01 | 100 | 100 | TE-01 | 100 |
| 707 | TE-91 | 807 | 451 | TE-91 | 551 | 375 | TE-41 | 475 |
| 130 | TE-41 | 937 | 241 | TE-22 | 792 | 220 | TE-91 | 695 |
| 63 | TE-81 | 1000 | 146 | TE-31 | 938 | 205 | TE-81 | 900 |
| | | | 62 | TE-41 | 1000 | 100 | TE-74 | 1000 |
| <u>Tartan Red</u> <u>2U5596R</u> | | | <u>Almond Green</u> <u>2U2774</u> | | | <u>Connaught Green</u> <u>248A53</u> | | |
| 100 | TE-01 | 100 | 100 | TE-01 | 100 | 100 | TE-01 | 100 |
| 690 | TE-53 | 790 | 292 | TE-41 | 392 | 609 | TE-41 | 709 |
| 181 | TE-66 | 971 | 270 | TE-74 | 662 | 229 | TE-21 | 938 |
| 29 | TE-91 | 1000 | 196 | TE-31 | 858 | 62 | TE-72 | 1000 |
| | | | 142 | TE-91 | 1000 | | | |
| <u>Fiesta Yellow</u> <u>2U7268</u> | | | <u>Island Blue</u> <u>2U2314</u> | | | <u>Carlton Gray</u> <u>2U1509</u> | | |
| 100 | TE-01 | 100 | 100 | TE-02 | 100 | 100 | TE-01 | 100 |
| 781 | TE-91 | 881 | 416 | TE-22 | 515 | 706 | TE-41 | 806 |
| 81 | TE-76 | 962 | 230 | TE-41 | 746 | 109 | TE-91 | 915 |
| 38 | TE-41 | 1000 | 192 | TE-91 | 938 | 85 | TE-74 | 1000 |
| | | | 62 | TE-66 | 1000 | | | |
| | | | <u>Tweed Gray</u> <u>2U1176</u> | | | | | |
| | | | 100 | TE-02 | 100 | | | |
| | | | 440 | TE-91 | 540 | | | |
| | | | 280 | TE-41 | 820 | | | |
| | | | 95 | TE-74 | 915 | | | |
| | | | 85 | TE-32 | 1000 | | | |

INTERMIXING FORMULAEBMC 1966/1967 PER-MAX FORMULAE

| | | | | | | | | |
|---|-------|------|---------------------------------------|-------|------|--|-------|------|
| <u>Grampian Gray</u> <u>2U1287</u> | | | <u>Florida Green</u> <u>2U3476</u> | | | <u>Healey Blue</u> <u>2U2869</u> | | |
| 100 | TE-02 | 100 | 100 | TE-01 | 100 | 100 | TE-01 | 100 |
| 421 | TE-41 | 521 | 712 | TE-91 | 812 | 641 | TE-15 | 741 |
| 257 | TE-91 | 778 | 110 | TE-31 | 922 | 119 | TE-27 | 860 |
| 104 | TE-51 | 882 | 40 | TE-42 | 962 | 100 | TE-13 | 960 |
| 97 | TE-74 | 979 | 38 | TE-77 | 1000 | 27 | TE-41 | 987 |
| 21 | TE-23 | 1000 | | | | 13 | TE-23 | 1000 |
| <u>Stone</u> <u>2U1471</u> | | | <u>Smoke Gray</u> <u>2U1310</u> | | | <u>Sherwood Green</u> <u>2U3785</u> | | |
| 100 | TE-01 | 100 | 100 | TE-01 | 100 | 100 | TE-01 | 100 |
| 368 | TE-91 | 468 | 623 | TE-91 | 723 | 505 | TE-41 | 605 |
| 210 | TE-41 | 678 | 144 | TE-41 | 867 | 210 | TE-74 | 815 |
| 165 | TE-74 | 843 | 93 | TE-77 | 960 | 163 | TE-91 | 978 |
| 157 | TE-78 | 1000 | 29 | TE-31 | 989 | 22 | TE-31 | 1000 |
| | | | 11 | TE-22 | 1000 | | | |
| <u>Dark British Racing Green</u> <u>2U3876</u> | | | <u>Chalk Blue</u> <u>2U2918</u> | | | <u>Colorado Red</u> <u>2U5623R</u> | | |
| 100 | TE-01 | 100 | 100 | TE-01 | 100 | 100 | TE-01 | 100 |
| 369 | TE-21 | 469 | 517 | TE-41 | 617 | 482 | TE-53 | 582 |
| 266 | TE-71 | 735 | 350 | TE-94 | 967 | 239 | TE-79 | 821 |
| 240 | TE-41 | 975 | 33 | TE-51 | 1000 | 113 | TE-42 | 934 |
| 25 | TE-94 | 1000 | | | | 66 | TE-91 | 1000 |
| <u>Maltese White</u> <u>2U9979</u> | | | <u>Maroon</u> <u>2U631R</u> | | | <u>Mineral Blue</u> <u>2U2957</u> | | |
| 100 | TE-01 | 100 | 100 | TE-02 | 100 | 100 | TE-01 | 100 |
| 729 | TE-94 | 829 | 740 | TE-63 | 840 | 225 | TE-41 | 325 |
| 106 | TE-77 | 935 | 78 | TE-81 | 918 | 218 | TE-21 | 543 |
| 64 | TE-42 | 999 | 62 | TE-92 | 980 | 195 | TE-66 | 738 |
| 1 | TE-78 | 1000 | 20 | TE-41 | 1000 | 172 | TE-94 | 910 |
| | | | | | | 90 | TE-22 | 1000 |
| <u>Old English White</u> <u>2U9938</u> | | | <u>Pale Primrose</u> <u>2U7480</u> | | | <u>Riviera Blue</u> <u>2U2745</u> | | |
| 100 | TE-01 | 100 | 100 | TE-01 | 100 | 100 | TE-01 | 100 |
| 723 | TE-94 | 823 | 710 | TE-94 | 810 | 509 | TE-22 | 609 |
| 111 | TE-77 | 934 | 122 | TE-76 | 932 | 209 | TE-94 | 818 |
| 62 | TE-42 | 996 | 46 | TE-74 | 978 | 101 | TE-41 | 919 |
| 4 | TE-51 | 1000 | 22 | TE-42 | 1000 | 81 | TE-23 | 1000 |